

Ficha Técnica



Alfombra Adhesiva Descontaminante CleanGuard® "Sticky Mat"



Propiedades físicas

Película / espesor de capa: **0,050 mm ($\pm$ 0,005 mm)**

Resistencia adhesiva (g / 25 mm): **350g ($\pm$ 30g) / adhesivo en la parte superior.**

700g ($\pm$ 30g) / adhesivo en la parte inferior.


Resistencia a la rotura (Kg / 10mm): **>1,2**

Capacidad de alargamiento (%) : **>250%**

Capacidad de eliminación de polvo (5 pasos con un peso de 100 kg.): **99,9%**

Resistencia al calor: **70°C $\pm$ 3°C / 48 min**

Resistencia al frío: **-13°C $\pm$ 3°C / 48 min**



Composición química general

COMPONENTE	FÓRMULA QUÍMICA	NÚMERO CAS	% EN PESO
Polietileno	(C ₂ H ₄) _n	9002-88-4	80 $\approx$ 84
Copolímero Acrílico (con agente antibacteriano incorporado)		35239-19-1 (2634-33-5) (1310-73-2) (57-55-6)	9 $\approx$ 10
Acetato de Etilo	CH ₃ COO C ₂ H ₅	141-78-6	5 $\approx$ 6
Tolueno		108-88-3	2 $\approx$ 4

Composición química del agente biocida PROXEL XL 2

COMPONENTE	FÓRMULA QUÍMICA	NÚMERO CAS	% EN PESO
1,2-Benisotizolin-3- ona	C ₇ H ₅ NOS	2634-33-5	5 $\approx$ 15
Hidróxido de sodio >2% - <5%	NaOH	1310-73-2	< 5%
Propilenglicol	C ₃ H ₈ O ₂	57-55-6	30 $\approx$ 50

Disponible en color AZUL.



Disponible en:
pedidos@ramossts.com

www.ramossts.com



Decontaminating Adhesive Mat “Sticky Mat”

Physical properties

Film / layer thickness: **0.050mm (± 0.005mm)**

Adhesive strength (g / 25mm):

350g (± 30g) / adhesive on top.

700g (± 30g) / adhesive on the bottom.

Resistance to breakage (Kg / 10mm): **> 1.2**

Elongation capacity (%): **> 250%**

Dust removal capacity (5 steps with 100 kg weight): **99.9%**

Heat resistance: **70 ° C ± 3 ° C / 48 min**

Cold resistance: **-13 ° C ± 3 ° C / 48 min**



General chemical composition

COMPONENT	CHEMICAL FORMULA	CAS NUMBER	% IN WEIGH
Polyethylene	(C ₂ H ₄) _n	9002-88-4	80 ≈ 84
Acrylic Copolymer (with incorporated antibacterial agent)		35239-19-1 (2634-33-5) (1310-73-2) (57-55-6)	9 ≈ 10
Ethyl acetate	CH ₃ COO C ₂ H ₅	141-78-6	5≈6
Toluene		108-88-3	2≈4

Chemical composition of the biocidal agent PROXEL XL 2

COMPONENT	CHEMICAL FORMULA	CAS NUMBER	% IN WEIGH
1,2-Benisotizolin-3- ona	C ₇ H ₅ NOS	2634-33-5	5 ≈ 15
Sodium hydroxide >2% - <5%	NaOH	1310-73-2	< 5%
Propylene glycol	C ₃ H ₈ O ₂	57-55-6	30 ≈ 50



Available in blue

Available in:
pedidos@ramossts.com

www.ramossts.com

